

TECHNICAL DATA SHEET

**PRODUCT:** 1170501

**DESCRIPTION:** WHITE ELASTIC ACRYLIC SEALER

**SUGGESTED USE:** EXTERIOR JOINERY

**APPLICATION DEVICES:** SPRAY GUN

**STORAGE:** KEEP CANS TIGHTLY SEALED, IN A WELL VENTILATED PLACE, WITH CONTROLLED TEMPERATURE BETWEEN 10 AND 30 °C

**SHELF LIFE:** 18 MONTHS FROM PRODUCTION DATE, IF STORED AS ABOVE

**PHYSICAL CHARACTERISTICS**

VISCOSITY @ 20 °C	sec. cup DIN 4	65 ± 10%
SPECIFIC GRAVITY @ 20°C	Kg/l	1.2 ± 1%
SOLIDS CONTENT	%	60 ± 1

**READY TO USE BLEND**

	<b>PARTS BY WEIGHT</b>	<b>PARTS BY VOLUME</b>
1170501	100	100
31005	20	20
91033	20	25

**POT LIFE** About 10 hours @ 20°C thinned at 30% with 910.3

**APPLICATION VISCOSITY FOR SPRAYING** 15 to 18 sec. cup DIN 4

**ALTERNATIVE THINNERS PURPOSE**

91073	for hot weather.
91022	can be used as a retarder, if necessary.

**SUBSTRATE**

Both veneers and solid wood. Suitable for naturally pale wood, or bleached with chemical whiteners, or stained with light shades.

**APPLICATION**

SUGGESTED COATING WEIGHT	100 - 140 gr/m <sup>2</sup>
SUGGESTED N° OF COATS	max 2 coats
TIME BETWEEN 2 COATS	45 min

**DRYING SCHEDULE AT ROOM TEMPERATURE**

	COATING WEIGHT 120 gr/m <sup>2</sup>
DUST FREE	30 min
TOUCH DRY	50 min
SANDABLE	10 hours

**GENERAL INFORMATION**

ELASIC WHITE SB ACRYLIC SEALER WITH EXCELLENT WETTING PROPERTIES AND LOW FIBRE RISING AND LOW PORE SWELLING.

THE PRODUCT IS PARTICULARLY SUITABLE FOR THE APPLICATION ON OUKUME' PLYWOOD FOR EXTERIOR.

THE PRODUCT MUST BE OVERCOATED, AFTER SANDING, WITH A WB TOP-COAT SUITABLE FOR EXTERIOR.

FOR HEALTH & SAFETY INFORMATION, PLEASE REFER TO RELEVANT MSDS.

**Revision** 2 dated 17 Dec 2012

1170501

This information is correct to the best of our knowledge. However, as the coating process depends on many variables and the actual application takes place without our supervision, we cannot assume any responsibility for the final result.