

ANTIQUUE EFFECT PATINA

sikkens

WOOD COATINGS

INTERIOR

TECHNOLOGY

Solventborne

PRODUCT TYPE

Stain

PRODUCT DESCRIPTION

Solventborne patina is always applied over a sealer. Possible to remove the excess of material with metal wool. To be also added to our Harmonising Stain Base to produce different colours with a harmonising wood effect.

- Fast drying
- Endless possibilities for different design effects
- Overcoat with Solventborne/Waterborne clear coat



COLOUR

Blue / Black / Scarlet Red / White / Yellow / Bronze Gold / Brown / Pale Gold / Silver / Walnut

PACK SIZES

1 L
5 L

SHELF LIFE

12 months

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

8-30% ±1 depending on colour

DENSITY (SPECIFIC WEIGHT)

0.80 - 1.05 +/- 1% depending on colour

DELIVER VISCOSITY

11 ± 1 Viscosity at delivery DIN 4 mm (sec.)

PREPARATION OF SUBSTRATES



Graduated sanding of wood Carefully remove the sanding dust. Coarse-pore wood must be brushed out.

P120,
P150,
P180

THINNING

TUP9500-F

APPLICATION METHOD

Spray application

APPLICATION

Spray pressure (bar)	1.0-1.5
Nozzle size (mm)	0.8-1.3
Thinner to be added (%)	100-200

DRYING TIME @ 20°C

Overcoatable	At least 10 minutes
--------------	---------------------

GENERAL INSTRUCTION

These products had been studied to obtain "aged effect". Removal should be done after 10-20 minutes with metal wool or with scotch brite weels

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-04-28 / 6